

CLAIMS

1. A method for manufacturing bleached mechanical and chemithermo-mechanical pulp including that lignocellulose material, preferably wood in chip form, is caused to pass through at least one preheater or through a chemical treatment system, a steam separator and a refiner in which the lignocellulose material is converted to a pulp suspension which, subsequent to steam separation, is passed at least to one storage vessel (latency chest) and to a screening department from which the major part of the pulp suspension is taken out as an essentially finished product or is taken out and passed to further treatment stages and in which reductive bleaching agent is added to the advancing pulp suspension without the use of a bleaching tower or like means,
2. A method according to Claim 1, characterized by adding complexing agent to the lignocellulose material upstream of and/or in said refiner.
3. A method according to Claims 1-2, characterized by passing the pulp suspension immediately subsequent to said steam separation to a second refiner for further refinement (defibration) of said pulp and from there to further steam separation.
4. A method according to Claim 3, characterized by adding complexing agent to the pulp suspension immediately upstream of and/or in said second refiner.
5. A method according to Claims 1-4, characterized by also passing the pulp suspension to a slusher (latency pulper) located immediately upstream of the storage vessel (the latency chest).

6. A method according to Claim 5, characterized by adding the bleaching agent to the pulp suspension in a pump located in connection with the slusher, said pump being caused to transport the pulp suspension to the storage vessel in a pipe.

Sub 3
5 7. A method according to Claims 1-6, characterized by causing reject pulp suspension from the screening department to pass through a refiner and thereafter through a slusher whereafter said reject pulp suspension is finally fed into the main pulp suspension flow, preferably upstream of and in connection with the storage vessel (the latency chest) or in the storage vessel (the latency chest).

8. A method according to Claim 7, characterized by adding bleaching agent to the reject pulp suspension at a location downstream of the refiner in that circuit and prior to introducing the reject pulp suspension into the main pulp suspension flow.

9. A method according to Claim 8, characterized in that the bleaching agent is a reducing bleaching agent.

Sub 4
15 10. A method according to Claims 8-9, characterized by adding the bleaching agent to the reject pulp suspension in a pump located in connection with the slusher in this circuit.

Sub B
20 11. A method according to Claims 1-10, characterized in that the temperature of the pulp suspension is very high from a bleaching aspect, preferably 80-95°C, at the location at which the bleaching agent is added and immediately downstream of said location, and in that the solid content or concentration is low, preferably 2-4%, at said location.

Sub 5
12. A method according to Claims 1-11, characterized in that the bleaching agent is dithionite, for instance sodium dithionite = $\text{Na}_2\text{S}_2\text{O}_4$.